

Material: BS 3100 Grade 420C28

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 3100 Grade 420C28 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.200 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	11.500 - 13.500
Nickel	Ni %	1.000 max.
Copper	Cu %	0.300 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	450 min.
Elongation in %	13 min.
Reduction of Area in %	-
Hardness in BHN	179 - 235
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
420C29	BS	British	Casting
420	SAE	USA	Sheet, Strip and Plate
420	AISI	USA	Forging
A 176 S42000	ASTM	USA	Steel Plate, Sheet and Strip
A 176 Type 420	ASTM	USA	Steel Plate, Sheet and Strip
A 314 420	ASTM	USA	Billets and Bars for Forging
A 314 S42000	ASTM	USA	Billets and Bars for Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India