

Material: BS 3100 Grade A3

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS 3100 Grade A3 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.450 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.050 max.
Sulphur	S %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	540 min.
Yield Strength in Mpa	295 min.
Elongation in %	14 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	18 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 216 WCB	ASTM	USA	Casting
SA 216 WCB	ASTM	USA	Casting
A660 Grade WCB	ASTM	USA	Casting
A660 Grade WCA	ASTM	USA	Casting
SA 216 WCA	ASME	USA	Casting
JO2502	UNS	USA	Casting
1.0619	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India