

Material: BS 3100 Grade AM2

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS 3100 Grade AM2 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.250 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	0.500 max.
Phosphorus	P %	0.050 max.
Sulphur	S %	0.050 max.
Chromium	Cr %	0.300 max.
Molybdenum	Mo %	0.150 max.
Nickel	Ni %	0.400 max.
Copper	Cu %	0.300 max.
Other	Ot %	0.800 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	400 - 490
Yield Strength in Mpa	215 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2074/C3	AS	Australia	Casting
1.622	ONORM	Australia	Casting
1.622	EN	European Union	Casting
1.622	BDS	Bulgaria	Casting
1.622	DIN	Germany	Casting
1.622	SS	Sweden	Casting
1.622	UNE	Spain	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India