

Material: BS 3100 Grade B4

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS 3100 Grade B4 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.250 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	0.300 - 0.700
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	2.500 - 3.500
Molybdenum	Mo %	0.350 - 0.600
Nickel	Ni %	0.400 max.
Copper	Cu %	0.300 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	370 min.
Elongation in %	13 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	25 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2074/H2A	AS	Australia	Casting
629	BS	British	Casting
B6	BS	British	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India