

Material: BS 310C40

Standard Specification for Austenitic Stainless Steel Castings for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 310C40 Austenitic Stainless Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.500	As - Cast	
Silicon	Si %	1.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	24.000 - 27.000		
Nickel	Ni %	19.000 - 22.000		
Molybdenum	Mo %	1.500 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	450 min.
			Yield Strength in Mpa	-
			Elongation in %	7 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J94224	UNS	USA	Casting
1.4848	DIN	Germany	Casting
G X 40 CrNi 26-20	UNI	Italy	Casting
422952	CSN	Czech Republic	Casting
40 CrNiSi 25-20	MSZ	Hungary	Casting
393 G X 40 CrNi 25-20	SFS	Finland	Casting
A297 Grade HK	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com