

Material: BS 316 S 17

Austenitic Stainless Steel Wire for Cold Forged Fasteners

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 3111-2 Austenitic Stainless Steel Wire for Cold Forged Fasteners

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Wire

Chemical Composition		
Carbon	C %	0.070 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.450 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	16.500 - 18.500
Nickel	Ni %	12.000 - 14.000
Molybdenum	Mo %	2.000 - 3.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	205 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4409	DIN	Germany	Casting
1.4409	EN	European Union	Casting
316	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging
SUS 316	JIS	Japan	Bar
03CH17N14M3	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging
A743 CF8M	ASTM	USA	Casting
A351 CF8M	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India