

Material: BS B 2

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS B 2 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.200 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	1.000 - 1.500
Nickel	Ni %	0.400 max.
Molybdenum	Mo %	0.450 - 0.650
Copper	Cu %	0.300 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Normalizing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	480 - 820
Yield Strength in Mpa	280 min.
Elongation in %	14 min.
Reduction of Area in %	-
Hardness in HB	140 - 241
Impact in Joule	10 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13052	UNS	USA	Casting
200-400 W	JIS	Japan	Casting
6120	AISI	USA	Forging, Bar, Wire, and Shape
B 4	BS	British	Forging
B 5	BS	British	Forging
B 6	BS	British	Forging
A732 5N	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India