

Material: BS EN 1706 AC-41000

Standard Specification for Aluminium and Aluminium Alloys - Castings

Group: Non-Ferrous Aluminium Alloy

Sub Group: BS EN 1706 Aluminium and Aluminium Alloys - Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Iron	Fe %	0.600 max.		
Magnesium	Mg %	0.450 - 0.650		
Manganese	Mn %	0.300 - 0.500		
Nickel	Ni %	0.050 max.		
Silicon	Si %	1.600 - 2.400		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.050 - 0.200		
Zinc	Zn %	0.100 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

Mechanical Properties	
Tensile Strength in Mpa	140 - 300
Yield Strength in Mpa	70 - 230
Elongation in %	3 - 10
Reduction of Area in %	-
Hardness in HB	50 - 95
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-41000	ASME	USA	Casting
EN AC-41000	DIN	Germany	Casting
EN AC-41000	SFS	Finland	Casting
Al Si2MgTi	ISO	International	Casting
EN AC-41000	UNE	Spain	Casting
EN AC-41000	UNI	Italy	Casting
EN AC-41000	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com