

Material: BS EN 1706 AC-43200

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: BS EN 1706 Aluminium and Aluminium Alloys - Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment															
Copper	Cu %	0.350 max.	As-Cast or Aging															
Iron	Fe %	0.650 max.																
Magnesium	Mg %	0.200 - 0.450																
Manganese	Mn %	0.550 max.																
Nickel	Ni %	0.150 max.																
Silicon	Si %	9.000 - 11.000																
Lead	Pb %	0.100 max.																
Titanium	Ti %	0.200 max.																
Zinc	Zn %	0.350 max.																
Other	Ot%	0.150 max.																
Aluminium	Al %	Balance	<table border="1"> <thead> <tr> <th colspan="2">Mechanical Properties</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength in Mpa</td> <td>160 - 240</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>80 - 200</td> </tr> <tr> <td>Elongation in %</td> <td>1 min.</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in HB</td> <td>50 - 80</td> </tr> <tr> <td>Impact in Joule</td> <td>-</td> </tr> </tbody> </table>		Mechanical Properties		Tensile Strength in Mpa	160 - 240	Yield Strength in Mpa	80 - 200	Elongation in %	1 min.	Reduction of Area in %	-	Hardness in HB	50 - 80	Impact in Joule	-
Mechanical Properties																		
Tensile Strength in Mpa	160 - 240																	
Yield Strength in Mpa	80 - 200																	
Elongation in %	1 min.																	
Reduction of Area in %	-																	
Hardness in HB	50 - 80																	
Impact in Joule	-																	
-	-	-																
-	-	-																
-	-	-																
-	-	-																
-	-	-																

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-43200	ASME	USA	Casting
EN AC-43200	DIN	Germany	Casting
Al Si10Mg (Cu)	ISO	International	Casting
EN AC-43200	UNI	Italy	Casting
EN AC-43200	AFNOR NF	France	Casting
EN AC-43200	UNE	Spain	Casting
EN AC-43200	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com