

Material: BS EN 1982 CuSn10Pb10-C (CC495K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.250 max.		
Manganese	Mn %	0.200 max.		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.500 max.		
Silicon	Si %	0.010 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.100 max.		
Lead	Pb %	8.000 - 11.000	Mechanical Properties	
Zinc	Zn %	2.000 max.	Tensile Strength in Mpa	180 min.
Tin	Sn %	9.000 - 11.000	Yield Strength in Mpa	80 min.
Cu + Ni	Cu%+Ni%	78.000 - 82.000	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	60 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com