

Material: BS EN 1982 CuSn11P-B (CB481K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.100 max.		
Manganese	Mn %	0.050 max.		
Nickel	Ni %	0.100 max.		
Lead	Pb %	0.250 max.		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.050 max.		
Silicon	Si %	0.010 max.		
Zinc	Zn %	0.050 max.		
Phosphorus	P %	0.500 - 1.000	Mechanical Properties	
Tin	Sn %	10.000 - 11.500	Tensile Strength in Mpa	250 min.
Copper	Cu %	87.000 - 89.500	Yield Strength in Mpa	130 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	60 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC481K	ONORM	Australia	Ingot and Casting
CC481K	AFNOR NF	France	Ingot and Casting
CC481K	BDS	Bulgaria	Ingot and Casting
CC481K	DIN	Germany	Ingot and Casting
CuSn11P-C	UNI	Italy	Ingot and Casting
CuSn11P-C	MSZ	Hungary	Ingot and Casting
CuSn11P-C	UNE	Spain	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com