

Material: BS EN 1982 CuSn12Ni2-B (CB484K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.200 max.		
Manganese	Mn %	0.200 max.		
Lead	Pb %	0.300 max.		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.100 max.		
Silicon	Si %	0.010 max.		
Zinc	Zn %	0.400 max.		
Silicon	Si %	0.010 max.		
Zinc	Zn %	0.500 max.		
Phosphorus	P %	0.050 - 0.400	Mechanical Properties	
Nickel	Ni %	1.500 - 2.500	Tensile Strength in Mpa	280 min.
Tin	Sn %	11.000 - 13.000	Yield Strength in Mpa	160 min.
Copper	Cu %	84.500 - 87.500	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
			Hardness in HBW	85 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC484K	AFNOR NF	France	Ingot and Casting
CuSn12Ni2-C	AFNOR NF	France	Ingot and Casting
CC484K	BDS	Bulgaria	Ingot and Casting
CuSn12Ni2-C	BDS	Bulgaria	Ingot and Casting
CC484K	DIN	Germany	Ingot and Casting
CuSn12Ni2-C	DIN	Germany	Ingot and Casting
CuSn12Ni2-C	UNI	Italy	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com