

Material: BS EN 1982 CuZn33Pb2Si-C (CC751S)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition		
Iron	Fe %	0.250 - 0.500
Nickel	Ni %	0.800 max.
Lead	Pb %	0.800 -2.200
Silicon	Si %	1.100 max.
Aluminium	Al %	0.100 max.
Manganese	Mn %	0.150 max.
Antimony	Sb %	0.050 max.
Tin	Sn %	0.800 max.
Cu + Ni	Cu%+Ni%	63.500 - 66.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	400 min.
Yield Strength in Mpa	280 min.
Elongation in %	5 min.
Reduction of Area in %	-
Hardness in HBW	110 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB751S	EN	European Union	Ingot and Casting
CB751S	DIN	Germany	Ingot and Casting
CB751S	UNI	Italy	Ingot and Casting
CB751S	BS	British	Ingot and Casting
CB751S	ONORM	Australia	Ingot and Casting
CB751S	AFNOR NF	France	Ingot and Casting
CB751S	CSN	Czech Republic	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India