

Material: BS EN 1982 CuZn37Al1-B (CB766S)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Antimony	Sb %	0.100 max.	As-Cast	
Tin	Sn %	0.500 max.		
Silicon	Si %	0.600 max.		
Lead	Pb %	0.500 max.		
Manganese	Mn %	0.500 max.		
Iron	Fe %	0.500 max.		
Nickel	Ni %	2.000 max.		
Aluminium	Al %	0.300 - 1.800		
Copper	Cu %	60.000 - 64.000	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	105 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC766S	AFNOR NF	France	Ingot and Casting
CC766S	BDS	Bulgaria	Ingot and Casting
CC766S	CSN	Czech Republic	Ingot and Casting
CC766S	SFS	Finland	Ingot and Casting
CuZn37Al1-C	ONORM	Australia	Ingot and Casting
CuZn37Al1-C	MSZ	Hungary	Ingot and Casting
CuZn37Al1-C	UNI	Italy	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com