

Material: BSI BS1400 LB2 CuSn10Pb10

Standard Specification for Copper Alloy and High Conductivity Conductivity Copper Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BSI BS1400 Copper Alloy and High Conductivity Conductivity Copper Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition		
Tin	Sn %	9.000 - 11.000
Zinc	Zn %	1.000 max.
Lead	Pb %	8.500 - 11.000
Phosphorus	P %	0.100 max.
Nickel	Ni %	2.000 max.
Iron	Fe %	0.150 max.
Aluminium	Al %	0.010 max.
Manganese	Mn %	0.200 max.
Antimony	Sb %	0.500 max.
Silicon	Si %	0.020 max.
Sulphur	S %	0.100 max.
Other	Ot%	0.500 max.
Copper	Cu %	Balance
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	190 min.
Yield Strength in Mpa	80 min.
Elongation in %	5 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
937B	AS	Australia	Ingot and Casting
C93700	AS	Australia	Ingot and Casting
CuPb10Sn10	ISO	International	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India