

Material: CSN 422952

Standard Specification for Alloy Steel Casting 42 2952

Group: Ferrous Stainless Steel Alloys

Sub Group: CSN 422952 Alloy Steel Casting 42 2952

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.300 - 0.450
Silicon	Si %	0.750 - 1.750
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	24.000 - 27.000
Nickel	Ni %	20.000 - 22.000
Molybdenum	Mo %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As - Cast

Mechanical Properties	
Tensile Strength in Mpa	441 min.
Yield Strength in Mpa	216 min.
Elongation in %	10 min.
Reduction of Area in %	-
Hardness in HB	130 - 220
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
310C40	BS	British	Casting
1.4848	DIN	Germany	Casting
G X 40 CrNi 26-20	UNI	Italy	Casting
J94224	UNS	USA	Casting
40 CrNiSi 25-20	MSZ	Hungary	Casting
393 G X 40 CrNi 25-20	SFS	Finland	Casting
A297 Grade HK	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India