

Material: DIN 1706 EN AC-51300

Standard Specification for Aluminium Alloy and Aluminium Alloys

Group: Non-Ferrous Aluminium Alloy

Sub Group: DIN 1706 Aluminium Alloy and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Magnesium	Mg %	4.300 - 6.800		
Silicon	Si %	0.550 max.		
Iron	Fe %	0.550 max.		
Manganese	Mn %	0.450 max.		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.100 max.		
Beryllium	Be %	0.005 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 150 - 180 Yield Strength in Mpa 80 - 100 Elongation in % 3 - 14 Reduction of Area in % - Hardness in HB 55 - 70 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM5	BS	British	Ingot and Casting
5230	IS	India	Casting
EN AC-51300	AFNOR NF	France	Ingot and Casting
EN AC-51300	EN	European Union	Ingot and Casting
EN AC-51300	ONORM	Australia	Ingot and Casting
EN AC-51300	BDS	Bulgaria	Ingot and Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com