

# Material: DIN 2.4060

## Standard Specification for Nickel and Nickel Alloy Castings

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** DIN 2.4060 Nickel and Nickel Alloy Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	0.150 max.
Manganese	Mn %	0.350 max.
Copper	Cu %	0.150 max.
Iron	Fe %	0.250 max.
Magnesium	Mg %	0.150 max.
Sulphur	S %	0.005 max.
Titanium	Ti %	0.100 max.
Ni + Co	Ni% + Co%	99.600 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
	As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	370 min.
Yield Strength in Mpa	100 min.
Elongation in %	1 min.
Reduction of Area in %	-
Hardness in HRB	100 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India