

Material: DIN 2.4110

Standard Specification for Nickel and Nickel Alloys Wires

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4110 Nickel and Nickel Alloys Wires

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Wire

Chemical Composition		
Carbon	C %	0.050 max.
Silicon	Si %	0.250 max.
Manganese	Mn %	1.500 - 2.500
Copper	Cu %	0.250 max.
Iron	Fe %	0.350 max.
Magnesium	Mg %	0.150 max.
Sulphur	S %	0.010 max.
Titanium	Ti %	0.100 max.
Ni + Co	Ni% + Co%	97.000 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	400 min.
Yield Strength in Mpa	140 min.
Elongation in %	2 min.
Reduction of Area in %	-
Hardness in HRB	220 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India