

Material: DIN 2.4856

Standard Specification for Nickel Strip, Sheet, Tube, Bar and Forging Alloy

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4856 Nickel Strip, Sheet, Tube, Bar and Forging Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Strip, Sheet, Tube, Bar and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	21.000 - 23.000		
Cobalt	Co %	1.000 max.		
Aluminium	Al %	0.400 max.		
Iron	Fe %	5.000 max.		
Nb + Ta	Nb% + Ta%	3.200 - 3.800		
Phosphorus	P %	0.010 max.	Mechanical Properties	
Sulphur	S %	0.010 max.	Tensile Strength in Mpa	690 - 1050
Titanium	Ti %	0.400 max.	Yield Strength in Mpa	275 min.
Nickel	Ni %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	240 max.
-	-	-	Impact in Joule	44 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
NiCr22Mo9Nb	DIN	Germany	Strip, Sheet, Tube, Bar and Forging
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com