

Material: DIN 25 CrMo 4

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 25 CrMo 4 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.220 - 0.290
Silicon	Si %	0.400 max.
Manganese	Mn %	0.600 - 0.900
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Chromium	Cr %	0.900 - 1.200
Molybdenum	Mo %	0.150 - 0.300
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Quenching + Tempering	
Mechanical Properties	
Tensile Strength in Mpa	
540 - 1400	
Yield Strength in Mpa	
345 - 440	
Elongation in %	
4 min.	
Reduction of Area in %	
50 min.	
Hardness in HB	
197 - 331	
Impact in Joule	
22 J @ RT	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-2	BS	British	Steel and Tube
1.7218	EN	European Union	Steel and Tube
1.7218	DIN	Germany	Steel and Tube
25 CrMo 4	AFNOR NF	France	Steel and Flat
25 CrMo 4	BS	British	Steel
25 CrMo 4	ISO	International	Steel and Tube
25 CrMo 4	UNI	Italy	Steel and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India