

Material: DIN EN 12164 CuBe2Pb (CW102C)

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: DIN EN 12164 CuBe2Pb Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Cobalt	Co %	0.300 max.	As Raw or Solution Heat Treated	
Lead	Pb %	0.200 - 0.600		
Iron	Fe %	0.200 max.		
Beryllium	Be %	1.800 - 2.000		
Nickel	Ni %	0.300 max.		
Other	Ot %	0.500 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 410 min. Yield Strength in Mpa 190 min. Elongation in % 12 min. Reduction of Area in % - Hardness in HV 120 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CW102C	BS	British	Rod
CuBe2Pb	BS	British	Rod
CW102C	UNE	Spain	Rod
CuBe2Pb	UNE	Spain	Rod
CW102C	NBN	Belgium	Rod
CuBe2Pb	NBN	Belgium	Rod
CW102C	AFNOR NF	France	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com