

Material: DIN EN 12844 ZP0810 I ZP8

Standard Specification For Zinc and Zinc Alloy Castings

Group: Non-Ferrous Zinc Alloys

Sub Group: DIN EN 12844 ZP0810 I ZP8 Zinc and Zinc Alloy Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.000 - 8.800	As-Cast	
Copper	Cu %	0.800 - 1.300		
Magnesium	Mg %	0.015 - 0.030		
Lead	Pb %	0.006 max.		
Cadmium	Cd %	0.006 max.		
Tin	Sn %	0.003 max.		
Iron	Fe %	0.060 max.		
Nickel	Ni %	0.020 max.		
Silicon	Si %	0.045 max.		
Zinc	Zn %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	370 min.
-	-	-	Yield Strength in Mpa	220 min.
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	100 min.
-	-	-	Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 240 ZA8	ASTM	USA	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com