

Material: DIN EN 1982 CuZn16Si4-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: DIN EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.100 max.	As-Cast	
Iron	Fe %	0.500 max.		
Manganese	Mn %	0.200 max.		
Nickel	Ni %	1.000 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.600 max.		
Antimony	Sb %	0.050 max.		
Silicon	Si %	3.000 - 5.000		
Tin	Sn %	0.250 max.		
Copper	Cu %	78.500 - 82.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 400 - 500 Yield Strength in Mpa 230 - 340 Elongation in % 5 - 10 Reduction of Area in % - Hardness in HB 100 - 190 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC761S	BS	British	Ingot and Casting
CB761S	EN	European Union	Ingot and Casting
CB761S	UNE	Spain	Ingot and Casting
CB761S	UNI	Italy	Ingot and Casting
CuZn16Si4-B	ONORM	Australia	Ingot and Casting
CuZn16Si4-B	MSZ	Hungary	Ingot and Casting
CuZn16Si4-B	AFNOR NF	France	Ingot and Casting

Disclaimer: **All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.**

Customer Care: +91-99090 45075 Email: info@icastllp.com