

# Material: DIN G X 40 CrNi 27-4

## Standard Specification for Corrosion Resistant Steel Castings

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** DIN G X 40 CrNi 27-4 Corrosion Resistant Steel Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.300 -0.500
Silicon	Si %	2.000 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	26.000 - 28.000
Nickel	Ni %	3.500 - 5.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	230 - 300
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G X 40 Cr 28	UNI	Italy	Casting
G X 35 CrNi 28-05	UNI	Italy	Casting
J92615	UNS	USA	Casting
1.4340	DIN	Germany	Casting
A 743 CC50	ASTM	USA	Casting
3444 Grade 9	IS	India	Casting
3444 Grade 13	IS	India	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India