

# Material: DIN G X 40 NiCrSi 35-25

## Standard Specification for Heat Resisting Steel Castings

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** DIN G X 40 NiCrSi 35-25 Heat Resisting Steel Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.300 - 0.500
Silicon	Si %	1.000 - 2.500
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	24.000 - 26.000
Nickel	Ni %	34.000 - 36.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As - Cast

Mechanical Properties	
Tensile Strength in Mpa	440 min.
Yield Strength in Mpa	-
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4857	DIN	Germany	Casting
N08705	UNS	USA	Casting
40 NiCrSi 35-25	MSZ	Hungary	Casting
G X 50 NiCrSi 35-25	UNI	Italy	Casting
SCH 24	JIS	Japan	Casting
A297 Grade HP	ASTM	USA	Casting
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India