

Material: DIN G-NiCu30Si3

Standard Specification for Nickel and Nickel-Copper Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4367 Nickel and Nickel-Copper Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.250 max.
Silicon	Si %	2.700 - 3.700
Magnesium	Mg %	0.120 max.
Copper	Cu %	27.000 - 33.000
Iron	Fe %	1.000 - 2.500
Aluminium	Al %	0.500 - 1.500
sulphur	S %	0.010 max.
Lead	Pb %	0.010 max.
Titanium	Ti %	0.200 max.
Other	Ot%	1.000 max.
Ni + Co	Ni% + Co%	61.000 - 68.000
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	650 min.
Yield Strength in Mpa	350 min.
Elongation in %	10 min.
Reduction of Area in %	-
Hardness in HB	220 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4367	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com