

Material: DIN GX 10 Ni 5

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing and Other Applications, for Low-Temperature Service

Group: Ferrous Mild Steel Alloys

Sub Group: DIN GX 10 Ni 5 Ferritic and Martensitic Steel Castings for Pressure-Containing and Low-Temperature Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment
Carbon	C %	0.060 - 0.120	
Silicon	Si %	0.600 max.	
Manganese	Mn %	0.500 - 0.800	
Phosphorus	P %	0.025 max.	
Sulphur	S %	0.020 max.	
Nickel	Ni %	4.500 - 5.500	
Iron	Fe %	Balance	
-	-	-	
-	-	-	
-	-	-	Normalizing or Annealing or Hardening + Tempering
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
Mechanical Properties			
			Tensile Strength in Mpa
			485 min.
			Yield Strength in Mpa
			275 min.
			Elongation in %
			24 min.
			Reduction of Area in %
			35 min.
			Hardness in BHN
			-
			Impact in Joule
			20 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
E2512	AISI	USA	Casting
Ao 10 Ni 20	MSZ	Hungary	Casting
2512	SAE	USA	Steel
AM 8 Ni 18	UNE	Spain	Casting
J41501	UNS	USA	Casting
1.5681	DIN	Germany	Casting
A757 B4N B4Q	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India