

Material: DIN H-Ni99,90

Standard Specification for Refined Nickel Alloy Castings

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN H-Ni99,90 Refined Nickel Alloy Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.030 max.
Cobalt	Co %	0.500 max.
Copper	Cu %	0.030 max.
Bismuth	Bi %	0.002 max.
Iron	Fe %	0.030 max.
sulphur	S %	0.030 max.
Lead	Pb %	0.005 max.
Antimony	Sb %	0.002 max.
Ni + Co	Ni% + Co%	99.900 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4021	DIN	Germany	Casting
Ni 9990	ISO	International	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com