

## Material: DIN H-Ni99,92

### Standard Specification for Refined Nickel Alloy Castings

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** DIN H-Ni99,92 Refined Nickel Alloy Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.030 max.
Cobalt	Co %	0.100 max.
Copper	Cu %	0.030 max.
Bismuth	Bi %	0.002 max.
Iron	Fe %	0.030 max.
sulphur	S %	0.005 max.
Lead	Pb %	0.001 max.
Antimony	Sb %	0.002 max.
Ni + Co	Ni% + Co%	99.920 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4019	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)