

Material: DIN NiCr 30 FeMo

Standard Specification for Nickel and Nickel-Iron Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCr 30 FeMo Nickel and Nickel-Iron Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.080 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	28.000 - 31.500		
Cobalt	Co %	5.000 max.		
Molybdenum	Mo %	4.000 - 6.000		
Iron	Fe %	13.000 - 17.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.020 max.		
Copper	Cu %	1.000 - 2.400		
			Mechanical Properties	
Niobium	Nb %	0.300 - 1.500	Tensile Strength in Mpa	-
Tungsten	W %	1.500 - 4.000	Yield Strength in Mpa	-
Nickel	Ni %	Balance	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4603	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com