

Material: DIN NiMo30

Standard Specification for Nickel and Nickel Alloy Forgings

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiMo30 Nickel and Nickel Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	1.000 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	4.000 - 7.000		
Copper	Cu %	0.500 max.		
Molybdenum	Mo %	26.000 - 30.000		
Phosphorus	P %	0.030 max.	Mechanical Properties	
Sulphur	S %	0.015 max.	Tensile Strength in Mpa	750 min.
Vanadium	V %	0.600 max.	Yield Strength in Mpa	320 min.
Nickel	Ni %	62.000 min.	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	260 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4810	DIN	Germany	Forging
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com