

Material: DIN S-NiMo15Cr

Standard Specification for Nickel and Nickel Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN S-NiMo15Cr Nickel and Nickel Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.500 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	2.000 - 7.000		
Cr + W	Cr% + W%	21.000 max.		
Molybdenum	Mo %	14.000 - 17.000		
Sulphur	S %	0.025 max.	Mechanical Properties	
Vanadium	V %	0.350 max.	Tensile Strength in Mpa	540 - 740
Tungsten	W %	5.000 max.	Yield Strength in Mpa	270 min.
Nickel	Ni %	50.000 min.	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4813	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com