

Material: DIN X 10 CrMoVNb 9-1

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: DIN X 10 CrMoVNb 9-1 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.080 - 0.120
Silicon	Si %	0.200 - 0.500
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.020 max.
Sulphur	S %	0.005 max.
Chromium	Cr %	8.000 - 9.500
Molybdenum	Mo %	0.850 - 1.050
Nickel	Ni %	0.300 max.
Vanadium	V %	0.180 - 0.250
Aluminium	Al %	0.040 max.
Nitrogen	N %	0.030 - 0.070
Niobium	Nb %	0.060 - 0.100
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment
Normalizing + Tempering

Mechanical Properties	
Tensile Strength in Mpa	520 - 850
Yield Strength in Mpa	435 min.
Elongation in %	17 min.
Reduction of Area in %	68 - 73
Hardness in BHN	-
Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4903	EN	European Union	Steel and Tube
1.4903	DIN	Germany	Steel
1.4903	DIN	Germany	Steel
91	BS	British	Steel and Tube
J84090	UNS	USA	Casting
X10CrMoVNb9-1	ISO	International	Steel and Tube
TU Z 10 CDVNb 09 01	AFNOR NF	France	Steel and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India