

Material: DIN X2CrNiMoCuN25-6-3

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: DIN X2CrNiMoCuN25-6-3 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Sheet, Plate and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.700 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	2.700 - 4.000
Nickel	Ni %	5.500 - 7.500
Copper	Cu %	1.000 - 2.500
Nitrogen	N %	0.150 - 0.300
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	690 - 1050
Yield Strength in Mpa	475 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HB	310 max.
Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4507	BS	British	Tube
1.4507	EN	European Union	Tube
1.4507	DIN	Germany	Steel, Sheet, Plate and Strip
X2CrNiMoCuN25-6-3	AFNOR NF	France	Steel
X2CrNiMoCuN25-6-3	UNI	Italy	Steel, Sheet, Strip and Plate
X2CrNiMoCuN25 6 3	EN	European Union	Steel and Tube
X3CrNiMoCuN25-7	AFNOR NF	France	Steel and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India