

# Material: EN 1.4307

## Standard Specification for Iron-Chromium-Nickel, Rod, Bar, Wire and Forging

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** EN 1.4307 Iron-Chromium-Nickel, Rod, Bar, Wire and Forging

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Rod, Bar, Wire and Forging

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	17.500 - 19.500
Nickel	Ni %	8.000 - 10.000
Nitrogen	N %	0.110 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	450 - 2100
Yield Strength in Mpa	175 min.
Elongation in %	12 min.
Reduction of Area in %	63 min.
Hardness in HB	215 max.
Impact in Joule	60 @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
304 S11	BS	British	Bright Bars, Hot Rolled and Cold Rolled, Coil
SUS 304L	JIS	Japan	Hot Rolled Equal Leg Angles
04CH 18N10	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging
304L	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging
1.4306	DIN	Germany	Cold Rolled, Strips, Slit, Coils and Forging
A743 CF3	ASTM	USA	Casting
A351 CF3	ASTM	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India