

Material: EN 1.5408

Standard Specification for Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion

Group: Ferrous Mild Steel Alloys

Sub Group: EN 1.5408 Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod, Bars, Wire and Extrusion

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 - 0.320	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.300 max.		
Manganese	Mn %	0.800 - 1.000		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	0.300 max.		
Boron	B %	0.0008 - 0.0050		
Molybdenum	Mo %	0.080 - 0.120		
Copper	Cu %	0.250 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	630 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	57 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J03011	UNS	USA	Casting
1.1811	DIN	Germany	Casting
161-480	BS	British	Casting
1030	AISI	USA	Forging, Bar, Wire, and Shape
SCPL1	JIS	Japan	Casting
A732 2Q	ASTM	USA	Casting
A732 2A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com