

# Material: EN 1.5430

## Standard Specification for Seamless Steel Tubes for Pressure Purposes

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** EN 1.5430 Seamless Steel Tubes for Pressure Purposes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.060 - 0.100
Silicon	Si %	0.600 max.
Manganese	Mn %	1.500 - 1.800
Phosphorus	P %	0.020 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	0.200 max.
Molybdenum	Mo %	0.300 - 0.400
Vanadium	V %	0.100 max.
Niobium	Nb %	0.050 max.
Nitrogen	N %	0.020 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing Forming

Mechanical Properties	
Tensile Strength in Mpa	500 - 650
Yield Strength in Mpa	350 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	80 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.5450	EN	European Union	Casting
1.545	EN	European Union	Casting
1.545	DIN	Germany	Casting
GS-8MnMo7 4	DIN	Germany	Casting
1.543	DIN	Germany	Casting
GS-8MnMo7 4	UNI	Italy	Casting
GS-8MnMo7 4	AFNOR NF	France	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India