

Material: EN 1.6783

Standard Specification for Heat Treatable Alloyed NiCrMo Steel

Group: Ferrous Mild Steel Alloys

Sub Group: EN 1.6783 Heat Treatable Alloyed NiCrMo Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 max.	Normalizing + Tempering or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	1.350 - 1.850		
Nickel	Ni %	2.500 - 3.500		
Molybdenum	Mo %	0.350 - 0.600		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	725 - 895
-	-	-	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	41 J @ -73°C

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-352 Grade LC2-1	ASME	USA	Casting
1.6783	DIN	Germany	Casting
20NCD12M	AFNOR NF	France	Casting
T15MoCrNi30R	STAS	Romania	Casting
J42215	UNS	USA	Casting
J42015	UNS	USA	Casting
A352 LC2-1	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com