

Material: EN 1.7380

Standard Specification for Flat Products for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: EN 1.7380 Flat Products for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar, Plate and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.140	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.400 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.100		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 - 630
-	-	-	Yield Strength in Mpa	250 min.
-	-	-	Elongation in %	17 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7375	DIN	Germany	Tube
J22090	UNS	USA	Casting
10 CD 9-10	AFNOR NF	France	Plate
10 CrMo 10	STAS	Romania	Tube
10 CrMo 9-10	MSZ	Hungary	Bar, Tube and Forging
10 CrMo 9-10	BS	British	Steel
A356 10	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com