

Material: EN 1.7779

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: EN 1.7779 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230	Quenching + Tempering	
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.300 - 0.500		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	3.000 - 3.300		
Nickel	Ni %	0.300 max.		
Molybdenum	Mo %	0.500 - 0.600		
Aluminium	Al %	0.040 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.450 - 0.550	Mechanical Properties Tensile Strength in Mpa 740 - 880 Yield Strength in Mpa 590 min. Elongation in % 14 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 27 J @ RT	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7779	EN	European Union	Steel and Tube
1.7779	DIN	Germany	Steel and Tube
20 CrMoV 13 5	DIN	Germany	Steel and Tube
20 CrMoV 13 5	MSZ	Hungary	Steel
15423	CSN	Czech Republic	Steel
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com