

Material: EN 1.8920

Standard Specification for Plates and Wide Flats Made of High Yield Strength Structural Steels

Group: Ferrous Mild Steel Alloys

Sub Group: EN 1.8920 Plates and Wide Flats Made of High Yield Strength Structural Steels

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.100 - 0.200
Silicon	Si %	0.150 - 0.350
Manganese	Mn %	0.600 - 1.000
Phosphorus	P %	0.025 max.
Sulphur	S %	0.250 max.
Chromium	Cr %	0.400 - 0.650
Nickel	Ni %	0.700 - 1.000
Molybdenum	Mo %	0.400 - 0.600
Copper	Cu %	0.150 - 0.500
Vanadium	V %	0.030 - 0.080
Boron	B %	0.0005 min.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
Annealing or Normalizing or Hardening + Tempering	

Mechanical Properties	
Tensile Strength in Mpa	795 min.
Yield Strength in Mpa	690 min.
Elongation in %	15 min.
Reduction of Area in %	30 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.8719	DIN	Germany	Steel
J12084	UNS	USA	Casting
6386 Type 12	AMS	USA	Steel
K11576	UNS	USA	Casting
SA-487 Grade 7A	ASME	USA	Casting
SA-592 Grade F	ASME	USA	Forging
A487 7A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com