

# Material: EN 10083-3 1.5531

## Standard Specification for Mild Steel Alloys Bar and Rod

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** EN 10083-3 1.5531 Mild Steel Alloys Bar and Rod

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bar and Rod

| Chemical Composition |      |                 | Heat Treatment                                                                                                                                                                                                       |  |
|----------------------|------|-----------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Carbon               | C %  | 0.270 - 0.330   | As Raw or Annealing or Normalizing or Hardening and Tempering                                                                                                                                                        |  |
| Silicon              | Si % | 0.400 max.      |                                                                                                                                                                                                                      |  |
| Manganese            | Mn % | 1.150 - 1.450   |                                                                                                                                                                                                                      |  |
| Phosphorus           | P %  | 0.025 max.      |                                                                                                                                                                                                                      |  |
| Sulphur              | S %  | 0.035 max.      |                                                                                                                                                                                                                      |  |
| Boron                | B %  | 0.0008 - 0.0050 |                                                                                                                                                                                                                      |  |
| Iron                 | Fe % | Balance         |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               | <b>Mechanical Properties</b><br>Tensile Strength in Mpa 800 - 950<br>Yield Strength in Mpa 650 min.<br>Elongation in % 13 min.<br>Reduction of Area in % -<br>Hardness in BHN As Per HT<br>Impact in Joule 60 J @ RT |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |
| -                    | -    | -               |                                                                                                                                                                                                                      |  |

| Cross Reference Table |          |                |                              |
|-----------------------|----------|----------------|------------------------------|
| Material              | Standard | Country        | Grade Belong to the Industry |
| 30MnB5                | EN       | European Union | Bar and Rod                  |
| 30MnB5                | ISO      | International  | Bar and Rod                  |
| 1.5531                | DIN      | Germany        | Bar and Rod                  |
| 30MnB5                | DIN      | Germany        | Bar and Rod                  |
| 1.5531                | BDS      | Bulgaria       | Bar and Rod                  |
| 30MnB5                | BDS      | Bulgaria       | Bar and Rod                  |
| 1.5531                | CSN      | Czech Republic | Bar and Rod                  |

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)