

Material: EN 10083-3 1.7227

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: EN 10083-3 1.7227 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.380 - 0.450	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 - 0.040		
Chromium	Cr %	0.900 - 1.200		
Molybdenum	Mo %	0.150 - 0.300		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	750 - 900
-	-	-	Yield Strength in Mpa	500 min.
-	-	-	Elongation in %	14 - 55
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	As Per HT
-	-	-	Impact in Joule	35 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
42CrMo4	EN	European Union	Bar and Rod
1.7225	EN	European Union	Bar and Rod
42CrMoS4	EN	European Union	Bar and Rod
P 1000 - 42CrMo4	AFNOR NF	France	Bar and Rod
P 880 - 42CrMo4	AFNOR NF	France	Bar and Rod
CMo 4 Z	MSZ	Hungary	Bar and Rod
F.1252	UNE	Spain	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com