

Material: EN 10083-3 34CrNiMo6

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: EN 10083-3 34CrNiMo6 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.380	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	1.300 - 1.700		
Molybdenum	Mo %	0.150 - 0.300		
Nickel	Ni %	1.300 - 1.700		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	800 - 950
-	-	-	Yield Strength in Mpa	600 min.
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	As Per HT
-	-	-	Impact in Joule	45 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.6582	EN	European Union	Bar and Rod
P 1000 - 34CrNiMo6	AFNOR NF	France	Bar and Rod
P 880 - 34CrNiMo6	AFNOR NF	France	Bar and Rod
1.6579	UNE	Spain	Bar and Rod
G35CrNiMo6-6	UNE	Spain	Bar and Rod
1.6579	SS	Sweden	Bar and Rod
G35CrNiMo6-6	SS	Sweden	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com