

Material: EN 10083-3 39NiCrMo3

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: EN 10083-3 39NiCrMo3 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 - 0.430	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.600 - 1.000		
Molybdenum	Mo %	0.150 - 0.250		
Nickel	Ni %	0.700 - 1.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	740 - 880
-	-	-	Yield Strength in Mpa	540 min.
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	As Per HT
-	-	-	Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.6510	EN	European Union	Bar and Rod
NCMo 4	MSZ	Hungary	Bar, Wire and Rod
1.651	BDS	Bulgaria	Bar and Rod
39 NiCrMo 3	CSN	Czech Republic	Bar and Rod
1.651	DIN	Germany	Bar and Rod
39 NiCrMo 3	DIN	Germany	Bar and Rod
1.651	SFS	Finland	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com