

Material: EN CW400J

Standard Specification for Copper and Copper Alloy Rod

Group: Non Ferrous Copper Alloys

Sub Group: EN CW400J Copper and Copper Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.	As Raw or Solution Heat Treated	
Manganese	Mn %	1.500 - 3.000		
Nickel	Ni %	6.000 - 8.000		
Lead	Pb %	2.300 - 3.300		
Tin	Sn %	0.200 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	47.000 - 50.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	500 min.
-	-	-	Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	115 - 200
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi7Zn39Pb3Mn2	DIN	Germany	Rod
CuNi7Zn39Pb3Mn2	ONORM	Australia	Rod
CW400J	ONORM	Australia	Rod
CuNi7Zn39Pb3Mn2	BDS	Bulgaria	Rod
CW400J	BDS	Bulgaria	Rod
CuNi7Zn39Pb3Mn2	CSN	Czech Republic	Rod
CW400J	CSN	Czech Republic	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com