

Material: EN CW607N

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: EN CW607N Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.200 max.		
Nickel	Ni %	0.300 max.		
Lead	Pb %	0.800 - 1.600		
Tin	Sn %	0.200 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	60.000 - 61.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	340 min.
-	-	-	Yield Strength in Mpa	140 - 509.9
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	62.5 min.
-	-	-	Hardness in HV	79 - 160
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn38Pb1	DIN	Germany	Rod
CuZn38Pb1	CSN	Czech Republic	Rod
CW607N	CSN	Czech Republic	Rod
CuZn38Pb1	ONORM	Australia	Rod
CW607N	ONORM	Australia	Rod
CuZn38Pb1	MSZ	Hungary	Rod
CW607N	MSZ	Hungary	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com