

Material: EN G 12 MoCrV 5 2

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: EN G 12 MoCr 5 2 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.150	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.450 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 - 0.500		
Molybdenum	Mo %	0.400 - 0.600		
Nickel	Ni %	0.400 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.220 - 0.300		
Tin	Sn %	0.025 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	510 - 660
-	-	-	Yield Strength in Mpa	295 min.
-	-	-	Elongation in %	17 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G12MoCrV5-2	BS	British	Plate, Tubes and Forging
G12MoCrV5-2	ISO	International	Casting
1.7720	ISO	International	Casting
G 12 MoCrV 5 2	CSN	Czech Republic	Casting
G 12 MoCrV 5 2	SFS	Finland	Casting
G 12 MoCrV 5 2	AFNOR NF	France	Casting
G 12 MoCrV 5 2	DIN	Germany	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com