

Material: EN G23Mn6

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: EN G23Mn6 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.200 - 0.250
Silicon	Si %	0.300 - 0.500
Manganese	Mn %	1.500 - 1.700
Phosphorus	P %	0.015 max.
Sulphur	S %	0.003 max.
Chromium	Cr %	0.300 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.1118	DIN	Germany	Casting
1.1119	EN	European Union	Casting
1.1119	DIN	Germany	Casting
GS-24Mn6	DIN	Germany	Casting
GS-23Mn6	DIN	Germany	Casting
1.1118	EN	European Union	Casting
GS-24Mn6	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com